



# STEFANO MARDEGAN

more than a fabric

Articolo Article	<b>MAR-MONOS CARBON AU ANTIBATTERICO</b>
------------------	--

Norma Norm	Descrizione Description	Valore Values	U.M.		Tolleranza Tolerances
	Composizione Composition	41 59	% %	PES PVC	
	Spessore - Thickness	≥ 0,45	mm		
DIN EN ISO 2060	Titolo	1100	dTex	Ordito Warp	
	Filato	1100	dTex	Trama Weft	
UNI EN ISO 2286-2	Peso - Weight	500	gr/m2		+/- 5%
EN ISO 2286-1	Altezza - Width	220	cm		+/- 1
ISO 1421 - 1998	Resistenza alla trazione	≥ 1750	N/5cm	Ordito Warp	
	Tensile strength	≥ 1450	N/5cm	Trama Weft	
UNI 4818 PT. 6°	Resistenza alla trazione	≥ 2800	N/5cm	Ordito Warp	
	Tensile strength	≥ 2500	N/5cm	Trama Weft	
UNI 4818 PT. 6°	Allungamento a Rottura	≥ 15	%	Ordito Warp	
	Elongation at Break	≥ 20	%	Trama Weft	
UNI 4818 PT. 9°	Resistenza alla lacerazione	≥ 300	N	Ordito Warp	
	Tear strength	≥ 300	N	Trama Weft	
	Trattamento antibatterico	SI			

UNI 9475 CSE RF 1/75/A	Resistenza al Fuoco Fire Resistance	Autoestinguente
---------------------------	--	-----------------

I valori sono indicativi - All values are given for information only

05/06/2020